

TECHNICAL DATA SHEET

BELGIQA VENEER PLANKS


OAK FIVE

- BQO501 Soft Greige
- BQO502 Warm Beige
- BQO503 Faded Tan
- BQO504 Medium Sand
- BQO505 Dark Dust
- BQO506 Light Sand
- BQO507 Faded Caramel
- BQO508 Smokey Hazel
- BQO509 Golden Brown
- BQO510 Dark Amber



001 PRODUCT DESCRIPTION

Wood type	European Oak
Finish	Color oil
Composition	Veneer (0,6 mm) - MDF (12 mm) – Veneer (0,6 mm)
Thickness	13 mm
Toplayer	0,6 mm
Width	150 - 180 - 220 - 260 - 300 mm
Length	3050 mm



002 GRADINGS



RIFT MIXMATCH



MIXMATCH



NATURAL GRADE



ART GRADE

003 GENERAL INFORMATION

Deviation in squareness	EN324-2, +-2 mm/m
Deviation in thickness	≤ 0.5 mm
Flexural strength	EN310, 20.0 +- 5 N/mm2
Adhesion wooden top layer	EN204/205, ≥ 1 N/mm2
Internal adhesion	EN319, 0.45 +- 0.05 N/mm2
Density	EN323, 700 +- 50 Kg/m3
Chemical resistance	EN 12720, see next page

004 SAFETY PROPERTIES

Fire classification	EN 13501-1, D-s1-d0
Formaldehyde emission	EN 717-1, E1
	TSCA Title VI compliant platform with NAF2 glue
REACH	Compliant
PCP (Pentachlorophenol)	CEN/TR 14823, <5 Ppm

005 CHEMICAL RESISTANCE

Active substance	Incubation period	Evaluation
Water	24 u	5
Cleaning agent	24 u	5
Ethanol	24 u	5
Acetic Acid	24 u	4
Red wine	24 u	5
Oil	24 u	5
Coffee	24 u	5
Milk	24 u	5
Mustard	24 u	5
Ammonia	2 min	5
Acetone	2 min	5
Assesment	Description	
5	No change	
4	Slight change	
3	Moderate change	
2	Clear change	
1	Strong change	