

TECHNICAL DATA SHEET

BELGIQA FLEXIBLE VENEER

OAK EIGHT

- BQO801 Light Porcelain

BQO802 Soft Chalk

BQO803 Soft Grey

BQO804 Warm Chalk

BQO805 Mineral Grey

BQO806 Rich Greige

BQO807 Warm Terra

BQO808 Intense Tan

BQO809 Warm Dust

BQO810 Mineral Brown
- BQO811 Madder Brown

BQO812 Warm Charcoal

BQO813 Silky Beige

BQO814 Rich Bronze

BQO815 Misty Greige

BQO816 Shadow Dust



001 PRODUCT DESCRIPTION

Wood type	European Oak
Finish	Multiple reactive stains, finished with hardwax oil
Composition	Veneer (1,5 mm) on phenolic paper backing
Thickness	1,5 mm
Width	1030 mm
Length	3050 mm

BELGIQA

ARCHITECTURAL WOOD PRODUCTS

002 GRADINGS



RIFT MIXMATCH



MIXMATCH

003 GENERAL INFORMATION

Deviation in dimensions	+10 / -0 mm/m
Deviation in thickness	≤ 0.3 mm
Adhesion wooden top layer	EN204/205, ≥ 1 N/mm2
Internal adhesion	EN319, 0.45 +- 0.05 N/mm2
Density	EN323, 700 +- 10 Kg/m3
Chemical resistance	EN 12720, see next page

004 SAFETY PROPERTIES

Fire classification	EN 13501-1, D-s1-d0
Formaldehyde emission	EN 717-1, E1
REACH	Conform
PCP (Pentachlorophenol)	CEN/TR 14823, <5 Ppm

005 CHEMICAL RESISTANCE

Active substance	Incubation period	Evaluation
Water	24 u	5
Cleaning agent	24 u	5
Ethanol	24 u	5
Acetic Acid	24 u	4
Red wine	24 u	5
Oil	24 u	5
Coffee	24 u	5
Milk	24 u	5
Mustard	24 u	5
Ammonia	2 min	5
Acetone	2 min	5
Assesment	Description	
5	No change	
4	Slight change	
3	Moderate change	
2	Clear change	
1	Strong change	